

Mr. J.E.Beddoes
 Pilkington Plyglass
 Cotes Park , Somercotes, Alfreton
 Derbyshire DESS 4 PL
 UNITED KINGDOM

Dow Corning Construction Industry System Laboratory Report - Sealant Adhesion

Date: 30 Jul 2008
Document ID: 0000045763
Job Number: 0000040189
Job Name: General Evaluation - 2008 - Pilkington Plyglass
Customer: Pilkington Plyglass
Customer Fax: +44 1773520052 john.beddoes@Pilkington.com

ADHESION TESTING (Modified ASTM C794) or (ETAG 002 Paragraph 8.3.2.4)

Dow Corning has completed adhesion testing / evaluation in support of the above referenced project. A summary of this laboratory testing / evaluation and application recommendations is given below.

1.Sample 65769	Substrate Description		
Substrate Type	Glass		
Substrate Description	Glass,Ref: Chromatics (New Product) Detail: Aluminum foil stuck to glass.		
Sealant	Cleaner	Primer	Application Recommendation
Dow Corning® 3362 Silicone Insulating Glass Sealant	Isopropanol	No Primer	Approved for Insulated Glazing
Dow Corning® 993 Structural Glazing Sealant	Isopropanol	No Primer	Approved for Structural Applications

Application recommendations are based on Dow Corning laboratory testing, evaluation and technical specifications.

The cleaning and priming recommendations are only valid for a period of 12 months, starting from the date of this letter (30 Jul 2008).

It is recommended that regular jobsite adhesion testing be performed throughout the project to confirm that good adhesion is obtained consistently on actual job site substrates. Information and literature on field adhesion testing and Dow Corning application procedures may be obtained by contacting your Dow Corning distributor or customer service representative.

For further information regarding these test results, please contact your Dow Corning Construction Field Specialist,

DOW CORNING CORPORATION
 Your Global Construction Connection @
www.dowcorning.com/construction

AMERICAS
 Sealant Test Lab, DC-4, Lab 3A4
 2200 W. Salzburg Road
 Auburn, MI 48611
 USA
 Tel: 989 496 5237
 Fax: 989 496 4374
 Americas.Coins@dowcorning.com


ASIA
 Songjiang Plant Dow Corning
 (Shanghai) Company, Ltd.
 448 Eastern Ave.
 Songjiang Industrial Zone
 Shanghai 201613, P. R. China
 Phone: 86 21 3774 1000
 Fax: 86 21 5774 3471
 Asia.Coins@dowcorning.com

EUROPE
 Dow Corning Europe S.A.
 Parc Industriel – Zone C
 7180 Senefte
 Belgium
 Phone: +32 64 88 80 00
 E-Fax: +32 2 706 50 59
 Europe.Coins@dowcorning.com

Guisepina CONTI, on at Seneffe, BELGIUM
E-mail: g.conti@dowcorning.com

Please review "Technical Information for Structural Applications using Dow Corning Silicone Sealants" communication dated December 17, 2007 and available upon request to your local Dow Corning representative or our Technical Information Center (eutech.info@dowcorning.com) which includes latest requirements in terms of quality control for Structural Glazing applications.

Sincerely
DOW CORNING CORPORATION



Fiby ALBERT
AETS Lab Leader

cc: Marie ELLIOTT, Dow Corning, Coventry UNITED KINGDOM